

COOLPRO® RPP36

GEOMEMBRANE

CoolPro® RPP36 | 36 mils

Coated Fabric	Standard	Metric
Thickness (+/- 10%)	36 mils	0.91 mm
Coating Type	Polypropylene	
Coating Distribution	50 / 50	

A variety of standard widths and colors are available including NSF 61 certified material.

Mechanical Properties	ASTM Test Methods	Standard	Metric
Breaking Strength (Warp / Fill)	D751A	275 / 250 lbs	1220 / 1110 N
Tear Strength (Warp / Fill)	D751B (mod)	70 / 70 lbs	311 / 311 N
Wide Width Strength (Warp / Fill)	D4885	150 / 125 lbs / in	262 / 219 N / cm
Hydrostatic Resistance	D751A	350 psi	2.4 MPa
Puncture Resistance	FTMS 101C, 2031	300 lbs	1330 N
Ply Adhesion	D751 (mod)	40 lbs / 2 in*	178 N / 5 cm*
Dimensional Stability	D1204	1 % max	
Low Temperature	D2136	-40°F	-40°C
Abrasion Resistance (H18 / 1 kg)	D3884	5,000 cycles	
Stress Crack Resistance	D1693	3,000 hrs	
UV Resistance (black)	G154	35,000 hrs	
Ozone Resistance (100 pphm / 14 days)	D1149	No Cracks	

Factory Seam Properties	ASTM Test Methods	Standard	Metric
Bonded Seam Strength	D7749	200 lbs	890 N
Peel Adhesion	D413	20 lbs / in*	35 N / cm*

* **COMMENT** - Ply Adhesion and Peel Adhesion testing may result in a film tearing bond (FTB) if the strength between layers is greater than the strength of the material itself.

A One-Stop Shop. Cooley is the leading provider of a complete range of commercial and potable water-grade geomembranes—including Coolpro® reinforced polypropylene, Coolthane® polyurethane coated fabrics, and Coolshield® for high-temperature and extreme containment applications—to provide cost-competitive solutions for a wide, highly diverse range of applications.



The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, no warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.

For further information, please contact Engineered Membranes: 401.724.9000 or eminfo@cooleygroup.com