

ARMORSEAL®

GEOMEMBRANE

ArmorSeal® TPO100B | 100 mil

Base Fabric	Standard	Metric
Weight	6.3 oz / yd ²	173 g / m ²
Fiber / Style	Polyester / Knit	

Coated Fabric	Standard	Metric
Thickness	100 (+/- 10) mils	2.54 (+/- 0.25) mm
Total Weight	68 (+/- 4) oz / yd ²	2,310 (+/- 102) g/m ²
Coating Type	Polypropylene Anti-static Formulation	
Coating Distribution	50 / 50	
Sealing Properties	Thermal	

Material Properties	ASTM Test Methods	Standard	Metric
Tensile Strength, Grab (Warp / Fill)	D751A	550 / 500 lbs	2,450 / 2,200 N
Tear Strength, Tongue (Warp / Fill)	D751B (mod)	120 / 100 lbs	400 / 445 N
Ply Adhesion	D751 (mod)	35 lbs / 2 in	156 N / 5 cm
Puncture, Screwdriver	D751	80 lbs	356 N
Puncture, 1" Ball	D751	550 lbs	2,450 N
Hydrostatic Resistance	D751A	600 psi	4.1 MPa
Dimensional Stability (1 hr / 180°F)	D1204	1% (max)	1% (max)
Low Temp	D2136	-60°F	-51°C
High Temp	D1204	180°F	82°C
UV Exposure (no cracks or crazing)	G154	15,000 hrs	
Lay Flat (edge height from floor)		0.25 in (max)	
Skew (roll deviation from straightness)		<0.25 in (max) per 10 ft length	

A variety of standard widths and colors are available.

This product uses blue antistatic pigment (Cooley part no CPG745).

A One-Stop Shop. Cooley is the leading provider of a complete range of commercial and potable water-grade geomembranes—including Coolpro® reinforced polypropylene, Coolthane® polyurethane coated fabrics, and Coolshield® for high-temperature and extreme containment applications—to provide cost-competitive solutions for a wide, highly diverse range of applications.



The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, no warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.

For further information, please contact Engineered Membranes: 401.724.9000 or eminfo@cooleygroup.com