

ARMORSEAL®

GEOMEMBRANE

ArmorSeal® TPO60B | 65 mil

Base Fabric	Standard	Metric
Weight	6.3 oz / yd ²	214 g / m ²
Fiber / Style	Polyester / Knit	

Coated Fabric	Standard	Metric
Thickness	65 (+/- 5) mils	1.65 (+/- 0.13) mm
Total Weight	43 (+/- 2) oz / yd ²	1,462 (+/- 68) g / m ²
Coating Type	Polypropylene Anti-static Formulation	
Coating Distribution	50 / 50	
Sealing Properties	Thermal	

Material Properties	ASTM Test Methods	Standard	Metric
Tensile Strength, Grab (Warp / Fill)	D751A	500 / 450 lbs	2,220 / 2,000 N
Tear Strength, Tongue (Warp / Fill)	D751B (mod)	120 / 100 lbs	534 / 445 N
Ply Adhesion	D751 (mod)	35 lbs / 2 in	156 N / 5 cm
Dimensional Stability	D1204	1% (max)	1%
Low Temp	D2136	-60°F	-51°C
High Temp	D1204	180°F	82°C
UV Exposure (no cracks or crazing)	G154	10,000 hrs	
Lay Flat (edge height from floor)		0.25 in (max)	
Skew (roll deviation from straightness)		<0.25 in (max) per 10 ft length	

A variety of standard widths and colors are available.

This product uses blue antistatic pigment (Cooley part no CPG745).

A One-Stop Shop. Cooley is the leading provider of a complete range of commercial and potable water-grade geomembranes—including Coolpro® reinforced polypropylene, Coolthane® polyurethane coated fabrics, and Coolshield® for high-temperature and extreme containment applications—to provide cost-competitive solutions for a wide, highly diverse range of applications.



The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, no warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.

For further information, please contact Engineered Membranes: 401.724.9000 or eminfo@cooleygroup.com