

### C3<sup>®</sup> PLUS

### COMMERCIAL ROOFING

#### C3<sup>®</sup> Plus 45 | 45 mils

Base Fabric	Standard	Metric
Base Fabric Weight	3.01 oz / yd <sup>2</sup>	102 g / m <sup>2</sup>
Fiber/Style	Polyester - Aramid / Knit	

Coated Fabric	Standard	Metric
Thickness, overall	45 (+/- 4) mils	1.14 (+/- 0.10) mm
Thickness, over scrim (min)	16 mils	0.41 mm
Coating Type	PVC / KEE	

Material Properties	ASTM Test Methods	Standard	Metric
Tensile Strength, Grab (Warp / Fill)	D751A	270 / 240 lbs	1,200 / 1,070 N
Tensile Elongation (Warp / Fill)	D751A	15% / 15%	
Tear Strength, Tongue (Warp / Fill)	D5884	45 / 45 lbs	200 / 200 N
<b>Properties After Oven Aging (retained)</b>			
Tensile Strength, Grab	D573	90%	
Tensile Elongation	D573	90%	
Puncture Strength (FTMS 101C)	Method 2031	300 lbs	1,330 N
Hydrostatic Resistance	D751	350 psi	2.4 MPa
Abrasion Resistance (H18 / 1 kg)	D3884	2,000 cycles	
Ply Adhesion (at Aramid edge)	D751	25 lbs / 2 in	111 N / 5 cm
Ozone Resistance (no cracks)	D1149	Pass	
Water Absorption	D471	< 3 %	
Dimensional Stability (1 hr / 100°C)	D1204	< 1 %	
Solar Reflectance (white)	C1549	0.86	
Solar Emittance (white)	E408	0.86	
Solar Reflective Index (white)	E1980	108	
<b>Properties After 2 yr Weathering (retained)</b>			
Tensile Strength, Grab	G90 / cycle 1	90%	
Tensile Elongation	G90 / cycle 1	90%	
Low Temp	D2136	-40°F	-40°C

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, no warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.

Elvaloy<sup>®</sup> is a registered trademark of E. I. du Pont de Nemours and Company

For further information, please contact Building Products:  
401.724.9000 or [bpinfo@cooleygroup.com](mailto:bpinfo@cooleygroup.com)