

C3[®]45

MODULAR ROOFING MEMBRANE

45 mils | 1.14 mm

Base Fabric	Standard	Metric
Base Fabric Weight	3.41 oz / yd ²	116 g / m ²
Fiber/Style	Polyester / Knit	

Coated Fabric	Standard	Metric
Thickness, overall	45 (+/- 4) mils	1.14 (+/- 0.10) mm
Thickness, over scrim (min)	16 mils	0.41 mm
Polymer Type	PVC / KEE	

Material Properties	ASTM Test Methods	Standard	Metric
Tensile Strength, Grab (Warp / Fill)	D751A	270 / 240 lbs	1,200 / 1,070 N
Tear Strength, Tongue (Warp / Fill)	D5884	45 / 45 lbs	200 / 200 N
Properties After Oven Aging (retained) Tensile Strength, Grab Tensile Elongation	D573		90% 90%
Puncture Strength (FTMS 101C)	Method 2031	300 lbs	1,330 N
Abrasion Resistance (H18 / 1 kg)	D3884	2,000 cycles	
Ply Adhesion	D751	14 lbs / 2 in	62 N / 5 cm
Ozone Resistance (no cracks)	D1149	Pass	
Water Absorption	D471	< 3 %	
Dimensional Stability (1 hr / 100°C)	D1204	< 1 %	
Solar Reflectance (white)	C1549	0.86	
Solar Emittance (white)	E408	0.86	
Solar Reflective Index	E1980	108	
Weathering Resistance (12,000 hrs)	G53	Pass	
Low Temp	D2136	-40°F	-40°C

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, no warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.

Elvaloy® is a registered trademark of E. I. du Pont de Nemours and Company

For further information, please contact Building Products:
401.724.9000 or bpinfo@cooleygroup.com