

ENVIROFLEX[®] RPE

High-Strength Reinforced Flexible Polyethylene

Applications

Liners, Covers, and Baffle
Curtains | Water Containment |
Construction Enclosures | Primary
and Secondary Containment

Added Benefits

Encapsulated edge
High strength polyester scrim
Flexible polyethylene polymer
High chemical resistance
UV resistant

Available Colors

Black | White | Custom Colors

Available Width

Up to 196 in. | 5 m

Available Thicknesses

10 | 14 | 20 | 24 | 30 | 36 | 45 | 60 mils

Available in standard and extra-strength

• **EnviroFlex[®] RPE** is a high-performing blend of flexible polyethylene
• polymers engineered with high-strength reinforced scrims for superior
• dimensional stability and advanced puncture and tear strengths. Its
• flexibility allows for improved quality control as well as pre-fabrication
• —providing cost and time savings, and reducing the need to construct
• on the field. These key features safeguard from expansion and contraction,
• providing a smoother installation process and maintaining uniformity in the
• membrane throughout the life of the project. EnviroFlex RPE's optimized
• product design is reliable and cost-effective, and Cooley's history of
• proven performance ensures consistent quality, responsive customer
• service, and dependable technical support.

*For further information,
please contact Cooley
Engineered Membranes*

Cooley Group
50 Esten Avenue
Pawtucket, RI 02860, USA
Tel: 1.401.724.9000
Email: eminfo@cooleygroup.com
cooleygroup.com

EnviroFlex® RPE | 30 mils

TECHNICAL SPECIFICATIONS

EnviroFlex® RPE is manufactured with a factory-encapsulated edge and is available in rolls up to five meters wide, requiring less seaming. It is designed for a diverse array of applications including:

- Pad liners
- Pit liners
- Pond/tank liners and covers
- Construction enclosures
- Primary and secondary containment

Base Fabric	Standard	Metric
Base Fabric Weight	1.5 oz / yd ²	51 g / m ²
Fiber/Style	Polyester / Knit	

Coated Fabric	Standard	Metric
Total Weight (nominal)	30 oz / yd ²	1,017 g / m ²
Thickness (nominal)	30 mils	0.76 mm
Coating Type	PE	
Coating Distribution	50 / 50	
Sealing Properties	Thermal	

Material Properties	ASTM Test Methods	Standard	Metric
Tensile Strength, Grab (Warp / Fill)	D751A	220 / 175 lbs	979 / 778 N
Tensile Strength, 1" Strip (Warp / Fill)	D751B	110 / 85 lbs	489 / 378 N
Tear Strength, Tongue (Warp / Fill)	D751B	55 / 20 lbs	245 / 89 N
Tear Strength, Trapezoidal (Warp / Fill)	D1117	90 / 55 lbs	400 / 245 N
Puncture Resistance	D4883	75 lbs	334 N
Hydrostatic Resistance	D751	255 psi	1.75 MPa
Dimensional Stability (180°F / 1h)	D1204	< 1.5%	
Low Temp Limit	D2136	-85°F	-65°C
High Temp Limit	D1204	180°F	82°C

A One-Stop Shop. Cooley is the leading provider of a complete range of commercial and potable water-grade geomembranes—including Coolpro® reinforced polypropylene, Coolthane® polyurethane coated fabrics, and Coolshield® for high-temperature and extreme containment applications—to provide cost-competitive solutions for a wide, highly diverse range of applications.



The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, no warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.