

# COOLGRIP® PVC WALKPAD

COMMERCIAL ROOFING

**80 mils (2 mm) | 150 mils (3.8 mm)**

CoolGrip® walkpad is a thick, textured PVC sheet used to protect roofing membrane in high traffic areas, such as around HVAC units that require regular maintenance.

### INSTALLATION

Heat-weld CoolGrip to the Cooley roofing membrane. Install the textured side up over the membrane with a 2-in (50.8 mm) continuous weld around the membrane perimeter to ensure water tightness.

Keep all pads at least 2 in (50.8 mm) from field fabricated seams, around penetrations, and adjacent walkpad. Ensure the walkpad is no longer than 10 ft when installed to allow for proper drainage. Avoid installing over the disc on mechanically fastened systems.

Physical Properties	80 mils (2 mm)	150 mils (3.8 mm)
Thickness (nominal)	80 mils (2 mm)	150 mils (3.8 mm)
Roll Size	36 in x 60 ft	36 in x 60 ft
Coverage	180 ft <sup>2</sup> /roll or 20 yd <sup>2</sup> /roll	180 ft <sup>2</sup> /roll or 20 yd <sup>2</sup> /roll
Weight per Roll	99 lbs (45 kg)	129 lbs (58 kg)

Material Properties	ASTM Test Methods	Standard	Metric
Tensile Strength, Grab (Warp / Fill)	D751A	200 / 200 lbs	890 / 890 N
Tear Strength, Tongue (Warp / Fill)	D751B	45 / 45 lbs	200 / 200 N
Dimensional Stability (1 hr / 212°F)	D1204	+/- 1%	
Ply Adhesion	D751 (mod)	14 lbs / 2 in	62 N / 5 cm
Screwdriver Puncture	D751	50 lbs	222 N
Abrasion Resistance (H18 / 1 kg)	D3884	10,000 cycles	
Coefficient of Friction (typical) (Dry / Wet)	C1028	1.0 Unit / 1.3 Units	
Low Temp	D2136	-40°F	-40°C
High Temp, Continuous Use	D1204	212°F	100°C

A variety of standard colors are available.

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, no warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.