

MEDGUARD™

MEDICAL MEMBRANE

MedGuard™ | 8.5 oz / yd² | 288 g / m²

Coated Fabric	Standard	Metric
Total Weight (nominal)	8.5 oz / yd ²	288 g / m ²
Coating Type	EVA	
Sealing Properties	Dielectric / Thermal	

Material Properties	ASTM Test Methods	Standard	Metric
Tensile Strength, Grab (Warp / Fill)	D751A	80 / 80 lbs	356 / 356 N
Tear Strength, Tongue (Warp / Fill)	D751B	40 / 40 lbs	178 / 178 N
Thermal Adhesion Strength	D751	15 lbs / in	26 N / cm
Low Temp	D2136	-50°F	-46°C
High Temp, Cont/Interm.	D1204	180 / 200°F	82 / 93°C

This is a preliminary specification based on limited data. Final production values may vary.

A variety of standard widths and colors are available.

A One-Stop Shop. Cooley is the leading provider of a complete range of commercial and potable water-grade geomembranes—including CoolPro® reinforced polypropylene, CoolThane® polyurethane coated fabrics, and CoolShield® for high-temperature and extreme containment applications—to provide cost-competitive solutions for a wide, highly diverse range of applications.



The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, no warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.

For further information, please contact Engineered Membranes: 401.724.9000 or eminfo@cooleygroup.com