



Americas • Asia • Europe • Middle East • Africa

## TECHNICAL DATA SHEET

### V-Care® Napp/28

Launderable fabric for use in incontinence care products and other applications requiring a barrier to moisture

#### COATED FABRIC SPECIFICATIONS\*

Total thickness (nominal)	19 mils
Total weight	8.4 oz/yd <sup>2</sup>
Coating type	Flexible Vinyl
Coating distribution	Single-coated
Sealing properties	<input checked="" type="checkbox"/> Dielectric <input type="checkbox"/> Thermal

\* A variety of standard widths and colors are available. Please contact Cooley Customer Service at [solutions@cooleysgroup.com](mailto:solutions@cooleysgroup.com) for more details.

#### MATERIAL PROPERTIES

PROPERTY	MINIMUM	TYPICAL	TEST METHOD
Grab Tensile (Warp)	55 lb/in	65 lb/in	ASTM D751
Grab Tensile (Fill)	34 lb/in	37 lb/in	ASTM D751
Trapezoid Tear (Warp)	14 lb	17 lb	ASTM D751
Trapezoid Tear (Fill)	13 lb	15 lb	ASTM D751
Laundry Shrinkage (Warp)		-3 %	Cooley TM-02
Laundry Shrinkage (Fill)		+1 %	Cooley TM-02
Flame Retardancy	Class 1		16 CFR 1610
	Meets requirements		CAN/CGSB-4.2 No. 27.5
Composition	71 % vinyl, 29 % polyester		ASTM D751

Comments:

Questions? Email: [solutions@cooleysgroup.com](mailto:solutions@cooleysgroup.com)

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, no warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.