

Americas • Asia • Europe • Middle East • Africa

## TECHNICAL DATA SHEET VinaGYM<sup>®</sup> 51-19

## Athletic Mat Cover

## COATED FABRIC SPECIFICATIONS\*

Total thickness (nominal) Total weight Coating type Coating distribution Sealing properties

20 mils 19.4 oz/yd<sup>2</sup> Flexible Vinyl 50% back / 50% face ⊠ Dielectric ⊠Thermal \* A variety of standard widths and colors are available. Please contact Cooley Customer Service at <u>solutions@cooleygroup.com</u> for more details.

MATERIAL PROPERTIES			
PROPERTY	MINIMUM	TYPICAL	TEST METHOD
Grab Tensile (Warp)	276 lb/in	309 lb/in	ASTM D751
Grab Tensile (Fill)	271 lb/in	302 lb/in	ASTM D751
Trapezoid Tear (Warp)	51 lb	71 lb	ASTM D751
Trapezoid Tear (Fill)	60 lb	84 lb	ASTM D751
Adhesion (Warp)	5 lb/in	10 lb/in	ASTM D751
Adhesion (Fill	5 lb/in	10 lb/in	ASTM D751
Flame Retardancy	Pass		NFPA 701 M2 flat
	Pass		CAN/ULC S-109 L&S
	Pass		Cal Title 19, Par 1237.1
	Class 1 or A		ASTM E84
Composition	79% vinyl, 21% polyester		ASTM D751

Comments:

Questions? Email: solutions@cooleygroup.com

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, no warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.