



Americas • Asia • Europe • Middle East • Africa

## TECHNICAL DATA SHEET

### Vintex® SoffPAK HB

#### Cover Fabric with *Soft Surface Technology*

#### COATED FABRIC SPECIFICATIONS\*

Total weight (nominal)	12.3 oz/yd <sup>2</sup>
Coating type	Flexible Vinyl
Coating distribution	50% back, 50% face
Sealing properties	<input checked="" type="checkbox"/> Dielectric <input checked="" type="checkbox"/> Thermal

\* A variety of standard widths and colors are available. Please contact Cooley Customer Service at [solutions@cooleygroup.com](mailto:solutions@cooleygroup.com) for more details.

#### MATERIAL PROPERTIES

PROPERTY	MINIMUM	TYPICAL	TEST METHOD
Grab Tensile (Warp)	185 lb/in	190 lb/in	ASTM D751
Grab Tensile (Fill)	110 lb/in	122 lb/in	ASTM D751
Trapezoid Tear (Warp)	30 lb	35 lb	ASTM D751
Trapezoid Tear (Fill)	20 lb	22 lb	ASTM D751
Adhesion (Warp)	6 lb/in	8 lb/in	ASTM D751
Adhesion (Fill)	4 lb/in	6 lb/in	ASTM D751
Abrasion Resistance (CS-17/500 g)	300 cycles	425 cycles	ASTM D3884
Composition	44% vinyl, 27% polyester, 27% Nylon		

Comments:

Questions? Email: [solutions@cooleygroup.com](mailto:solutions@cooleygroup.com)

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, no warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.