

ARMORSEAL®

GEOMEMBRANE

ArmorSeal® L4513KU | 45 oz / yd² | 243 g / m²

Base Fabric	Standard	Metric
Weight	7.14 oz / yd ²	243 g / m ²
Fiber / Style	Polyester / Leno	

Coated Fabric	Standard	Metric
Total Weight	45 (+/- 4) oz / yd ²	1,530 (+/- 136) g/m ²
Coating Type	PVC	
Coating Distribution	55 / 45	
Sealing Properties	Dielectric / Thermal	

Material Properties	ASTM Test Methods	Standard	Metric
Tensile Strength, Grab (Warp / Fill)	D751A	600 / 350 lbs	2,670 / 1,560 N
Tear Strength, Tongue (Warp / Fill)	D751B (mod)	130 / 150 lbs	578 / 667 N
Hydrostatic Resistance	D751A	500 psi	3.4 MPa
Puncture, Screwdriver	D751	130 lbs	578 N
Puncture, Ball	D751	1,000 lbs	4,450 N
Ply Adhesion	D751 (mod)	16 lbs / 2 in	71 N / 5 cm
Low Temp	D2136	-40°F	-40°C
High Temp, Cont/Interm.	D1204	180 / 200°F	82 / 93°C
Abrasion Resistance (Wheel H18 / 1 kg)	D3884	10,000 cycles	

This product meets the flame resistance requirements of the California State Fire Marshall. Registration No. F-10204.

A One-Stop Shop. Cooley is the leading provider of a complete range of commercial and potable water-grade geomembranes—including Coolpro® reinforced polypropylene, Coolthane® polyurethane coated fabrics, and Coolshield® for high-temperature and extreme containment applications—to provide cost-competitive solutions for a wide, highly diverse range of applications.



The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, no warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.

For further information, please contact Custom Solutions: 401.724.9000 or custom@cooleygroup.com