## Cooley / CUSTOM SOLUTIONS

## **ARMORSHELL®**

GEOMEMBRANE

## ArmorShell® L1810KUP | 21 mils

Base Fabric	Standard	Metric
Weight	2.8 oz / yd²	95 g / m²
Fiber / Style	Polyester / Knit	

<b>Coated Fabric</b>	Standard	Metric
Thickness	21 (+/- 2) mils	0.53 (+/- 0.05) mm
Total Weight	18 (+/- 1.5) oz / yd²	612 (+/- 51) g/m <sup>2</sup>
Coating Type	PVC	
Coating Distribution	50 / 50	
Sealing Properties	Dielectric / Thermal	

Material Properties	ASTM Test Methods	Standard	Metric	
Tensile Strength, Grab (Warp / Fill)	D751A	200 / 190 lbs	890 / 845 N	
Tear Strength, Tongue (Warp / Fill)	D751B (mod)	60 / 80 lbs	267 / 356 N	
Puncture, Screwdriver	D751	45 lbs	200 N	
Puncture, Ball	D751	275 lbs	1,220 N	
Hydrostatic Resistance	D751A	250 psi	1.7 MPa	
Ply Adhesion	D751 (mod)	10 lbs / 2 in	44 N / 5 cm	
RF Adhesion	D751	12.5 lbs / in	22 N / cm	
Thermal Adhesion	D751	12.5 lbs / in	22 N / cm	
Low Temp	D2136	-40°F	-40°C	
High Temp, Cont/Interm.	D1204	180 / 200°F	82 / 93°C	
Abrasion Resistance (Wheel H18 / 1 kg)	D3884	500 cycles		
Flame Resistance, Afterflame Time	FTMS 191A, Method 5903	2 sec	2 sec (max)	
Flame Resistance, Char Length	FTMS 191A, Method 5903	6 in (max)	15 cm (max)	

Listed with the California State Fire Marshall. Passes NFPA 701 (large scale). Special anti-static compound with expected range of  $1.2 \times 10^{10}$  to  $4.3 \times 10^{10}$  ohms surface resistivity. This product is RoHS compliant.

A One-Stop Shop. Cooley is the leading provider of a complete range of commercial and potable water-grade geomembranes—including Coolpro® reinforced polypropylene, Coolthane® polyurethane coated fabrics, and Coolshield® for high-temperature and extreme containment applications—to provide cost-competitive solutions for a wide, highly diverse range of applications.



The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, no warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.

For further information, please contact Custom Solutions: 401.724.9000 or custom@cooleygroup.com