

COOLGUARD® MPK36

CONTAINMENT

CoolGuard® MPK36 | 36 mils

Coated Fabric	Standard	Metric
Total Weight (nominal)	34 oz / yd ²	1,153 g / m ²
Thickness (+/- 10%)	36 mils	0.91 mm
Coating Type	Ethylene Interpolymer Alloy (EIA)	
Coating Distribution	50 / 50	
Sealing Properties	Dielectric, Thermal	

Material Properties	ASTM Test Methods	Standard	Metric
Tensile Strength, Grab (Warp / Fill)	D751A	250 / 200 lbs	1,112 / 890 N
Tensile Strength, 1" Strip (Warp / Fill)	D751B	130 / 120 lbs / in	228 / 210 N / cm
Tear Strength, Tongue (Warp / Fill)	D751B (mod)	40 / 30 lbs	178 / 133 N
Puncture, Flat Tip	D4833	95 lbs	423 N
Puncture, Ball	D751	350 lbs	1,557 N
Puncture, Pyramid	FTMS 101C, 2031	200 lbs	890 N
Hydrostatic Resistance	D751A	350 psi	2.41 MPa
Dimensional Stability (180°F / 1 hr)	D1204	2.5% max.	
Ply Adhesion	D751 (mod)	20 lbs / 2 in	88 N / 5 cm
Thermal Adhesion	D751 (mod)	15 lbs / in	26 N / cm
Low Temp Bend	D2136	-25°F max.	-32°C max.
Abrasion Resistance (H18 / 1 kg)	D3389	5,000 cycles	

A variety of standard widths and colors are available.

A One-Stop Shop. Cooley is the leading provider of a complete range of commercial and potable water-grade geomembranes—including CoolPro® reinforced polypropylene, CoolThane® polyurethane coated fabrics, and CoolShield® for high-temperature and extreme containment applications—to provide cost-competitive solutions for a wide, highly diverse range of applications.

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, no warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.

For further information, please contact Containment Solutions: 401.724.9000 or containment@cooleygroup.com