

COOLPRO® RPP45

GEOMEMBRANE

CoolPro® RPP45 | 45 mils

Scrim Reinforced Polypropylene

Meets GRI GM-18 / FGI RPP Specification
Certified to NSF/ANSI/CAN 61 and AS/NZS 4020

Coated Fabric	Standard	Metric
Thickness (+/- 10%)	45 mils	1.1 mm
Coating Type	Polypropylene	
Coating Distribution	50 / 50	

Mechanical Properties	ASTM Test Methods	Standard	Metric
Breaking Strength (Warp / Fill)	D751A	300 / 250 lbs	1330 / 1110 N
Breaking Elongation (Warp / Fill)	D751A	22%	
Tear Strength (Warp / Fill)	D751B (mod)	70 / 70 lbs	311 / 311 N
Hydrostatic Resistance	D751A	350 psi	2.4 MPa
Puncture Resistance (Pyramid)	FTMS 101C, 2031	300 lbs	1334 N
Puncture Resistance (Flat Tip)	D4833	85 lbs	378 N
Ply Adhesion	D751 (mod)	40 lbs / 2 in*	178 N / 5 cm*
Dimensional Stability	D1204	1 % max	
Low Temperature	D2136	-40°F	-40°C
Abrasion Resistance (H18 / 1 kg)	D3389	7,500 cycles	
Stress Crack Resistance	D1693	3,000 hrs	
UV Resistance (black)	G154	40,000 hrs	

Factory Seam Properties	ASTM Test Methods	Standard	Metric
Bonded Seam Strength	D7749	200 lbs	890 N
Peel Adhesion	D6636	20 lbs / in*	35 N / cm*

* **COMMENT** - Ply Adhesion and Peel Adhesion testing may result in a film tearing bond (FTB) if the strength between layers is greater than the strength of the material itself.

A variety of standard widths and colors are available including material certified to NSF/ANSI/CAN 61.

A One-Stop Shop. Cooley is the leading provider of a complete range of commercial and potable water-grade geomembranes—including CoolPro® reinforced polypropylene, CoolThane® polyurethane coated fabrics, and CoolShield® for high-temperature and extreme containment applications—to provide cost-competitive solutions for a wide, highly diverse range of applications.

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, no warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.

For further information, please contact Containment Solutions: 401.724.9000 or containment@cooleygroup.com