

C3[®] Plus PVC | 80 mils

TECHNICAL DATA

COATED FABRIC SPECIFICATIONS*

Revision Date: 26 Oct 2021
Expiry Date: 26 Oct 2026

Thickness, overall	80±8 mils
Thickness, over scrim (min)	28 mils
Coating Type	PVC/KEE

PROPERTY		MINIMUM	TYPICAL	TEST METHOD
Tensile Strength, Grab	Warp/Fill	270 / 240 lbs	335 / 335 lbs	ASTM D751A
Tensile Elongation, Grab	Warp/Fill	15 / 15%	20 / 20%	ASTM D751A
Tear Strength, Tongue	Warp/Fill	45 / 45 lbs	65 / 60 lbs	ASTM D5884
Puncture Strength (FTMS 101°C)		300 lbs	400 lbs	Method 2031
Hydrostatic Resistance		350 psi	450 psi	ASTM D751
Abrasion Resistance (H18/1kg)		2,000 cycles	3,500 cycles	ASTM D3884
Ply Adhesion (at Aramid edge)		25 lbs/2"	30 lbs/2"	ASTM D751
Water Absorption		<3%	<2%	ASTM D471
Dimensional Stability (1 hr/100°C)		<1%	<0.5%	ASTM D1204
Low Temperature Bend		-40°F		ASTM D2136
Ozone Resistance (no cracks)		Pass		ASTM D1149
Properties After Oven Aging (retained)				ASTM D573
Tensile Strength		90% (minimum)		ASTM D751A
Tensile Elongation		90% (minimum)		ASTM D871A
Properties after 2 yr Weathering (retained)				ASTM G90/cycle 1
Tensile Strength		90% (minimum)		ASTM D751B
Tensile Elongation		90% (minimum)		ASTM D751B
Solar Reflectance (white)		0.86		ASTM C1549
Solar Emittance (white)		0.86		ASTM E408
Solar Reflective Index (white)		108		ASTM E1980

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, no warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.