

COOLEY® TRICOT



Class A Protective Fabric

Ultra soft high-loop face with maximum protection for sensitive auto parts

Applications

Dunnage Bags | Transport Slings | Liners

Features & Benefits

Class “A” surface friendly

Offered in single-face, dual-face, and foam-cushioned options for tailored protection.

Adhesive-free construction prevents damage from glue seepage common in laminated bags

Softer face than common rigid laminated alternatives

Unbroken loop tricot eliminates potential for tricot filaments to transfer onto parts

.....

Cooley’s Tricot fabrics deliver Class “A” surface protection while guarding against scratches and marring. The ultra-soft tricot knit surfaces cushion items with a high-loop face, offering superior performance to rigid laminated alternatives. The extrusion-coated scrim resists tearing and delamination, even in low temperatures. An adhesive-free design and continuous loops prevent filament transfer, ensuring clean, durable, and reliable protection for all handling and transport applications.

KRC2 features a single tricot face that provides gentle cushioning and a soft, protective surface—balanced by a durable single-scrim backing for reliable strength.

KRK2 offers tricot knit on both sides and a double-scrim construction that delivers enhanced strength while maintaining an ultra-soft surface.

Tricot Foam incorporates soft foam middle layers for added cushioning, giving parts extra impact resistance and enhanced protection while preserving surface safety.

With Cooley’s Tricot fabrics, you get flexible, high-performance fabrics that combine surface safety, cushioning, and durability—available in versatile options to suit your specific protection needs.

Cooley Group
350 Esten Avenue
Pawtucket, RI 02860
Tel: +1 401.724.9000
Email: custom@cooleygroup.com
cooleygroup.com

Tricot KRK2 | 13.8
Dunnage bag fabric with tricot knit on both sides

TECHNICAL DATA

COATED FABRIC SPECIFICATIONS*

Revision Date: 3 Nov 2024
Expiry Date: 3 Nov 2029

Total Thickness (nominal)	23 mils
Total Weight	13.8 oz/yd ²
Coating Type	Flexible Vinyl
Coating Distribution	50% back / 50% face
Sealing Properties	Dielectric Thermal

* A variety of standard widths and colors are available.

PROPERTY	MINIMUM	TYPICAL	TEST METHOD
Grab Tensile (Warp)	160 lb/in	175 lb/in	ASTM D751
Grab Tensile (Fill)	170 lb/in	200 lb/in	ASTM D751
Trapezoid Tear (Warp)	40 lb	50 lb	ASTM D751
Trapezoid Tear (Fill)	35 lb	45 lb	ASTM D751
Adhesion (Warp)	1.0 lb/in	2.3 lb/in	ASTM D751
Adhesion (Fill)	1.5 lb/in	2.6 lb/in	ASTM D751
Composition	60 % vinyl, 40 % polyester		ASTM D751

Comments: This is a preliminary specification based on limited data. Final production values may vary.

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, no warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.