

TXN® 226

TECHNICAL DATA

COATED FABRIC SPECIFICATIONS*

Weight (nominal)	22 oz/yd ²
Coating Type	PVC
Base Fabric	1500 x 1500 denier Polyester
Sealing Properties	Dielectric Thermal

* A variety of standard widths and colors are available.

Revision Date: 12 Jan 2022
Expiry Date: 12 Jan 2027

PROPERTY	MINIMUM	TYPICAL	TEST METHOD
Tensile Strength, Grab (warp/fill)	500 / 500 lbs	545 / 485 lbs	ASTM D751A
Tensile Strength, 1" Strip (warp/fill)	320 / 280	415 / 345 lbs	ASTM D751B
Tongue Tear Strength (warp/fill)	55 / 45	115 / 90 lbs	ASTM D5884
Ply Adhesion	10 lbs/2 in	15 lbs/2 in	ASTM D751
Thermal Adhesion	17 lbs/in	24 lbs/in	ASTM D751
Shrinkage	1.5% (max)	1.0% (max)	ASTM D1204
Low Temperature Bend	-40°F		ASTM D2136
High Temperature (continuous/intermittent)	160 / 180°F		ASTM D1204

Comments:

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, no warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.