

COOLTECT®



Applications

Liners and Covers | Baffle Curtains |
Construction Enclosures | Primary &
Secondary Containment

Added Benefits

Encapsulated Edge
High-Strength Polyester Knit Scrim
Flexible Polyethylene Polymer
High-Chemical Resistance
Excellent UV Resistance

Available Colors

Black | Tan | White
Custom colors available upon request



.....

CoolTect® RPE is a high-performance, flexible, scrim-reinforced polyethylene designed for a wide range of applications, including pad liners, pit liners, pond/tank liners and covers, construction and industrial enclosures, as well as primary and secondary containment. Available in rolls up to five meters wide, it minimizes seaming and enhances installation efficiency. Its flexibility supports improved quality control and easy pre-fabrication—resulting in significant cost and time savings by reducing the need for on-site construction.

Featuring a high-strength, polyester-knitted scrim, CoolTect delivers excellent dimensional stability and outstanding resistance to punctures, tears, expansion, and contraction. This ensures smoother installations, minimal wrinkling, and long-term membrane integrity. A proprietary extrusion process encapsulates the scrim edges by applying polymer directly to the reinforcement, providing superior performance over coated or laminated alternatives.

Certified to NSF Standard 61 and AS 4020 for potable water usage.

**For more information, please contact
Cooley Containment Solutions**

Cooley Group
350 Esten Avenue
Pawtucket, RI 02860
Tel: +1 401.724.9000
containment@cooleygroup.com
cooleygroup.com

CoolTect® RPE30 | 30 mils

TECHNICAL DATA

COATED FABRIC SPECIFICATIONS*

Revision Date: 8 May 2025
Expiry Date: 16 Aug 2026

Total Thickness	30±2 mils
Thickness over scrim (min)	10 mils
Total Weight (nominal)	21 oz/yd²
Coating Type	Polyethylene
Sealing Properties	Thermal

PROPERTY		MINIMUM	TYPICAL	TEST METHOD
Tensile Strength, Grab	warp/fill	250 / 250 lbs	300 / 350 lbs	ASTM D7004
Tensile Elongation, Grab	warp/fill	25 / 25%	30 / 30%	ASTM D7004
Tensile Strength, 1" Strip	warp/fill	160 / 195 lbs	180 / 215 lbs	ASTM D751B
Tensile Elongation, 1" Strip	warp/fill	22 / 22%	25 / 25%	ASTM D751B
Tear Strength, Tongue	warp/fill	70 / 70 lbs	90 / 130 lbs	ASTM D5884
Puncture, Rod		75 lbs	90 lbs	ASTM D4833
Hydrostatic Resistance		345 psi	365 psi	ASTM D751
Ply Adhesion strength		20 lbs/in	30 lbs/in	ASTM D751
Shrinkage (180°F/1 hr)		<1%	0.5%	ASTM D1204
Low Temperature Bend		-70°F	-70°F	ASTM D2136
Abrasion Resistance (H18/1 kg)		5,000 cycles	6,000 cycles	ASTM D3389
Oxidative Induction Time		100 minutes	385 minutes	ASTM D8117
Hydraulic Conductivity		1.0 x 10 ⁻¹¹ cm/sec		ASTM E96
Seam Shear Strength		90 lbs/in	97 lbs/in	ASTM D7747
Seam Peel Strength		20 lbs/in	36 lbs/in	ASTM D7747

Comments:

- This product is certified to NSF/ANSI/CAN 61 and AS/NZS 4020 for potable water containment.
- This product is certified to AS4020 and NSF Std 61 for potable water containment.
- This product meets the requirements of GRI GM-25 (Category 3 – Standard) specification.
- This product is safe for fish and plants and passes the following USEPA Chronic Toxicity Screening tests: EPA 1000.0, EPA 1002.0, EPA 2000, and EPA 2021.0

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, no warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.